



Table 704.6.2A - Gradation Requirements

Percent Passing (Square Openings)										
Aggregate Class	8" (200)	2 1/2" (63)	2" (50)	1 1/2" (37.5)	1" (25)	3/4" (19)	#4 (4.75)	#40 (425µm)	#100 (150 µm)	#200 (75 µm)
1				100		50-90	20-50	5-20		0-7.0
2				100		80-100	35-75	10-30		0-10.0
3				100		50-90	20-50	5-20		4.0-12.0
4				100		50-95	20-60	5-35		
5			100				30-90			0-25.0
6				100		50-100	25-70	10-45	3-28	
7	90-100		0-5							
8				100		80-100	35-75	10-40		4.0-14.0
9		100		80-95		50-70	20-40			0-8.0
10*					100	70-100	30-75	8-40		4.0-20.0